



# VAPOR-SAFE® Coating 30-80

Product Data Sheet

## PROPERTIES

### COLOR:

White

### APPLICATION CONSISTENCY:

Brush, airless spray.

### AVERAGE WEIGHT / U.S. GALLON (ASTM D1475):

11.5 lbs. (1.38 kg/l)

### AVERAGE NON-VOLATILE (ASTM D2369):

58% by volume (70% by weight)

### COVERAGE RANGE:

Subject to the type of surface being coated. Wet coverages shown below are for smooth non-porous surfaces. Porous or rough surfaces may require higher gallonage to attain required dry thickness. 4 -6 gallons per 100 square feet (1.6 - 2.4 l/m<sup>2</sup>) 0.064 in. to 0.096 in. wet thickness (1.6 to 2.4 mm)

### DRYING TIME 73°F (23°C) 50% RH:

Set to Touch: 4 Hours

Dry Through: 24 Hours

### SERVICE TEMPERATURE LIMITS:

Temperature at coated surface.

-20°F to 180°F (-29°C to 82°C)

### WATER VAPOR PERMEANCE (TYPICAL AVERAGE):

ASTM E 96, Procedure A:

0.05 perms (0.03 metric perms) at 47 mils dft (1.2 mm)

0.03 perms (0.02 metric perms) at 73 mils dft (1.9mm)

ASTM F 1249: 0.08 perms (0.05 metric perms) at 37 mils dft (0.94 mm). Tested at 100°F (38°C) and 90% RH.

### WET FLAMMABILITY:

Flash Point: None to boiling, 212°F (100°C)

### SURFACE BURNING CHARACTERISTICS (ASTM E84):

Flame Spread: 15

Smoke Developed: 30

Tested at coverage rate of 25 sq. ft./gal. (0.61 m<sup>2</sup>/l) in a 4" strip.

Applied to 1/4 inch (6.4 mm) inorganic reinforced cement board.

The flame spread may vary at different product thicknesses and/or when applied over other surfaces.

**VAPOR SAFE COATING** meets NFPA 90A and 90B 25/50 requirements.

™ Trademark of H.B. Fuller Construction Products Inc.

Visit us on the web at [www.fosterproducts.com](http://www.fosterproducts.com)

## FOSTER® VAPOR-SAFE® COATING

**FOSTER® VAPOR-SAFE® COATING** is a water-based, fire-resistant, flexible, high solids vapor barrier finish for most types of thermal insulation, including polystyrene foam. It may be used over dry concrete and finishing cement.

**VAPOR-SAFE® COATING** has the low water vapor permeance normally found in only solvent-based products. It can be used in high humidity environments, and greatly retards water vapor permeation. It is non-flammable in the wet state.

**VAPOR-SAFE® COATING** is formulated for both indoor and light duty commercial outdoor use. It is U.V. resistant. It has a mild latex "paint type" odor, and is designed for use over insulation on pipes, vessels, ducts, and equipment operating at cryogenic up to ambient temperatures.

**VAPOR-SAFE® COATING** is ideal for vapor sealing ASJ, FRK, and FSK jackets and board facings at joints, laps and over staple and weld pin punctures. It is an excellent duct board closure sealant. Do not exceed 1/8" (3.2 mm) wet film thickness.

**VAPOR-SAFE® COATING** meets the requirements of Military Specification MIL-PRF-19565C, Type II using method ASTM E96 Procedure A permeance and is QPD-19565 Listed.

**VAPOR-SAFE® COATING** meets the permeance requirements of ASTM C755 for below ambient vapor retarder coatings.

**VAPOR-SAFE® COATING** contains no asbestos, lead, mercury, or mercury compounds.

**VAPOR-SAFE® COATING 30-80** meets the requirements of:

- MAS Certified Green®
- California Dept. of Public Health Standard Method v1.2
- VOC Emissions and Content requirements to contribute to LEED v4 EQ Credit: Low Emitting Materials – Paints and Coatings
- Collaborative for High Performance Schools EQ 7.1

VOC Content: 33 g/l, less water and exempt solvents.



### LIMITATIONS

Store and apply between 40°F (4°C) and 100°F (38°C), protect from freezing until dry.

To resist rain washoff, allow at least 8-12 hours drying time above 50°F (10°C), with a relative humidity of 50%. Higher humidity and/or lower temperature may retard drying.

Always select VAPOR-SAFE® Coating in the white color for use over polystyrene on outdoor installations. After exposure, 30-80 may weather to an off-white color.

Always test foil and paper facings for acceptable adhesion before using.

Outdoor horizontal surfaces must always drain completely. A pitch of at least 1/2" per foot (4 cm/m) is required.

For heavy duty outdoor applications select VAPOR-SAFE® Mastic 30-90 or Foster 60-90 Monolar® Mastic.

**H.B. Fuller Construction Products Inc.**

1105 South Frontenac Street • Aurora, IL 60504 • 800-832-9002 • fax 800-952-2368

# APPLICATION GUIDE FOR FOSTER® VAPOR-SAFE® COATING 30-80™

## MATERIAL PREPARATION

Stir well, DO NOT THIN. Apply only to clean, dry, oil-free surfaces. Keep container closed when not in use.

## APPLICATION - INDOOR AND LIGHT DUTY OUTDOOR

To prevent water vapor and moisture infiltration, proper and complete flashing is required. Follow flashing specifications.

1. Apply tack coat of Foster VAPOR-SAFE® Coating (color as selected) at 2 to 4 gallons per 100 square feet (0.8 – 1.6 l/m<sup>2</sup>).
2. Embed Foster MAST-A-FAB® white membrane into the wet tack coat. Smooth membrane to avoid wrinkles and overlap all seams at least two inches (5 cm). Apply finish coat of VAPOR-SAFE® Coating, within 1/2 hour of the tack coat application, at 2 gallons per 100 square feet (0.8 l/m<sup>2</sup>).
3. This application shall provide a minimum dry film thickness of 37 to 56 mils (0.9 – 1.4 mm).
4. Do not use with canvas or other closed weave cloth.

## BRUSH

Use a good brush (suitable for water-based paints), making strokes as long as possible over the surface. Apply with full brush and spread out evenly. Do not overwork.

## SPRAY

VAPOR-SAFE® Coating may be airless spray applied. For spray equipment information, please consult Airless Spray Recommendations or contact your airless spray equipment supplier. Average viscosity range: 60,000 - 90,000 cps. Corrosion resistant pumps and fittings are suggested.

## CLEAN-UP

Use fresh water for cleaning brushes and equipment before product dries. Dry product may be removed with hot soapy water (with ammonia added) or strong solvents such as chlorinated solvent (non-flammable) or xylol (flammable).

## CUSTOMER SERVICE: 800-832-9002

IMPORTANT: H.B. Fuller Construction Products Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser or as otherwise provided on the certificate of analysis.

**For professional use only. Keep out of reach of children.  
Consult Safety Data Sheet and container label for further information.**