



### **PROPERTIES**

### COLOR:

Red

Other colors available on special order.

### APPLICATION CONSISTENCY:

Spray, Brush, Roller

### AVERAGE WEIGHT / U.S. GALLON (ASTM D 1475):

6.5 lbs. (0.77 kg/l)

### **AVERAGE NON-VOLATILE (ASTM D 1644):**

20% by volume (28% by weight)

### **COVERAGE RANGE (FSTM 72):**

(Subject to type of surface and nature of material being bonded.)

300-500 sq. ft./gal. (7.4 to 12.3 m2/l) 0005 in. to 0.003 in. wet film thickness (0.13 mm to 0.08mm)

### **BONDING TIME RANGE (FSTM 66):**

0 to 15 minutes

### **SERVICE TEMPERATURE LIMITS (FSTM 70):**

(Temperature at coated surface) -20°F to 200°F (-29°C to 93°C)

### WET FLAMMABILITY (ASTM D 93):

Flash point less than 20°F (-7°C)

# SURFACE BURNING CHARACTERISTICS (ASTM E 84):

Flame Spread: 10 Smoke Developed: 25

Tested at coverage rate of 200 sq. ft./gal. (4.9 m2/l). Applied to 1/4 inch (6.4 mm) inorganic reinforced cement board. The flame spread may vary at different product thicknesses and/or when applied over other surfaces.

™ Trademark of H.B. Fuller Construction Products Inc.

Visit us on the web at www.fosterproducts.com

# FOSTER DUCT-FAS® ADHESIVE (FLAMMABLE)



**FOSTER DUCT-FAS ADHESIVE** is a red quick-setting, synthetic elastomer insulation adhesive. It has been designed for use in attaching low density (up to 3#) duct liner, duct wrap, and fibrous glass insulation to sheet metal. It uses a flammable solvent system.

**DUCT-FAS ADHESIVE** has full coverage spray characteristics with conventional or airless spray equipment with little tendency to cobweb. Its high solids and gel-like consistency make it ideal for vertical or overhead surfaces and for brush or roller application.

**DUCT-FAS ADHESIVE** meets ASTM C 916, Type IV (ASC-A-7001A, Type IV) and NFPA 90A and 90B 25/50 requirements.

**DUCT-FAS ADHESIVE** is produced under the classification and follow-up service of Underwriters Laboratories, Inc.

**DUCT-FAS ADHESIVE** contains no asbestos, lead, mercury, or mercury compounds.

### **LIMITATIONS**

Store and apply between 40°F (4°C) and 100°F (38°C).

Always test plastic and painted materials for compatibility when using a solvent base product.

Allow to dry to a solvent-free condition before installing weld pins.

Not suggested for sealing vapor barrier jackets.

Overhead applications may require mechanical fasteners.

## APPLICATION GUIDE FOR FOSTER DUCT-FAS® ADHESIVE 85-22 (FLAMMABLE)

### **MATERIAL PREPARATION**

Stir well. DO NOT THIN. Apply only to clean dry surfaces. Keep container closed when not in use to prevent solvent evaporation. If stored below 60°F, the product should be conditioned in its unopened container at room temperature for at least 24 hours before usage.

### **APPLICATION**

Clean all surfaces thoroughly. Make sure the surfaces are free of any oil residue. Spray apply a uniform coverage of adhesive to one surface at 300-500 sq. ft./gal. (7.4 to 12.3 m2/l). While the adhesive is still wet, combine substrates with sufficient pressure to ensure 100% contact.

### SPRAY EQUIPMENT SUGGESTIONS

	MODEL	FLUID	AIR	FLUID	ATOMIZATION
	SPRAYGUN	NOZZLE	CAP	PRESSURE	PRESSURE
Binks	2001SS	63BSS	63PB	15-20 psi	40-50 psi
DeVilbiss	JGA-510	FF	777	15-20 psi	40-50 psi

Average viscosity: 2000-3500 cps.

### **CLEAN-UP**

Use a chlorinated solvent (non-flammable) or xylol (flammable).

## DATA REPRODUCED FROM UNDERWRITERS' LABORATORIES, INC. BUILDING MATERIALS DIRECTORY



## ADHESIVES SURFACE BURNING CHARACTERISTICS

Applied to Inorganic Reinforced Cement Board

Flame Spread: 10 Smoke Developed: 25

Tested as applied at a coverage rate of 200 ft<sup>2</sup>/gal Flash point of liquid adhesive (closed cup) less than -20 F 312U

### CUSTOMER SERVICE—800-832-9002

IMPORTANT: H.B. Fuller Construction Products Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTIBILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is six months from date of shipment to the original purchaser.

For professional use only. Keep out of reach of children.

Consult Material Safety Data Sheet and container label for further information.