



## PROPERTIES

**COLOR:**

White

**APPLICATION CONSISTENCY:**

Brush or spray

**AVERAGE WEIGHT / U.S. GALLON (ASTM D1475):**

10.4 lbs. (1.25 kg/l)

**AVERAGE NON-VOLATILE (ASTM D2369):**

40% by volume (51% by weight)

**COVERAGE RANGE:**

Subject to the type of surface being coated. Wet coverages shown below are for smooth non-porous surfaces. Porous or rough surfaces may require higher gallonage to attain required dry thickness.

40 – 70 sq. ft. per gal. (1.0 – 1.7 m<sup>2</sup>/l) per coat

0.040 in. – 0.023 in. wet film thickness

(1.0 – 0.6 mm) per coat

**DRYING TIME 73°F (23°C) 50% RH:**

Set to Touch: 2 Hours

Dry Through: 15 Hours

**SERVICE TEMPERATURE LIMITS:**

Temperature at coated surface

0°F to 180°F (-18°C to 82°C)

**WATER VAPOR PERMEANCE (TYPICAL AVERAGE):**

ASTM F1249: 0.5 - 1.5 perms (0.9 metric perms) at 31 mils dry film thickness (0.8 mm)

**WET FLAMMABILITY:**

No flash to boiling, 212°F (100°C)

**SURFACE BURNING CHARACTERISTICS (ASTM E84):**

Flame Spread: 10

Smoke Developed: 5

Tested at coverage rate of 40 sq. ft./gal. (1.0 m<sup>2</sup>/l). Applied to 1/4 inch (6.4 mm) inorganic reinforced cement board. The flame spread may vary at different product thicknesses and/or when applied over other surfaces.

**LIMITATIONS**

Store and apply between 40°F (4°C) and 100°F (38°C), protect from freezing until dry.

Always test foil and paper facings for acceptable adhesion before using.

## FOSTER® SEALFAS® COATING

**Foster® Sealfas® Coating** is a white, fire-resistive, tough, washable, abrasion-resistant indoor coating for thermal insulation. It is also used as a lagging and lap adhesive for canvas and glass lagging cloth. It has excellent brushing characteristics, which will result in better coverage, and more uniformly coated surfaces. It presents a neat white finish, and will not yellow or become discolored with age. The surface can be washed free of grease, oil, soot and other dirt accumulation.

**Sealfas® Coating** provides a protective finish for insulation on air conditioning ducts and cold water piping when applied in 2 coats with reinforcing fabric embedded between coats. When relative humidity exceeds 75% for continuous periods, or where the insulated piping or equipment contains chilled water, brine or refrigerant, additional vapor barrier protection is suggested.

**Sealfas® Coating** is compatible with polystyrene and polyurethane foam insulations. It may be applied to the joint or edges of fibrous duct liner insulations to seal and prevent air erosion.

**Sealfas® Coating** meets the requirements of Military Specification MIL-A-3316C Class 1, Grade A, and is listed on the QPL.

**Sealfas® Coating** is approved by the U.S. Coast Guard under 164.012.

**Sealfas® Coating** is produced under the classification and follow-up service of Underwriter's Laboratories, Inc. and meets NFPA 90A and 90B 25/50 requirements.

**Sealfas® Coating** contains no asbestos, lead, mercury or mercury compounds.

**Sealfas® Coating 30-36™** meets the requirements of:

- MAS Certified Green®
- California Dept. of Public Health Standard Method v1.2
- VOC Emissions and Content requirements to contribute to **LEED v4** EQ Credit: Low Emitting Materials – Paints and Coatings
- Collaborative for High Performance Schools EQ 7.1

VOC Content: 15 g/l, less water and exempt solvents.



™ Trademark of H.B. Fuller Construction Products Inc.

Visit us on the web at [www.fosterproducts.com](http://www.fosterproducts.com)

**H.B. Fuller Construction Products Inc.**

1105 South Frontenac Street    o    Aurora, IL 60504    o    800-832-9002    o    fax 800-952-2368

# APPLICATION GUIDE FOR FOSTER® SEALFAS® COATING 30-36™

## MATERIAL PREPARATION

DO NOT THIN. Apply only to clean, dry, oil-free surfaces. Keep container closed when not in use.

## APPLICATION

1. Apply a tack coat of Foster® Sealfas® Coating at 60 – 70 sq. ft. per gal. (1.5 – 1.7 m<sup>2</sup>/l).
2. Immediately imbed the selected lagging fabric into the wet coating. Smooth to avoid wrinkles and overlap seams by at least 2 inches (5 cm).
3. Immediately apply a finish coat at 60 – 70 sq. ft. per gal. (1.5 – 1.7 m<sup>2</sup>/l). The dry film thickness of this application will vary with the fabric selected.

For air conditioning ducts, increase the coverage rate to 40 – 50 sq. ft. per gal. (1.0 – 1.2 m<sup>2</sup>/l) for each coat.

## BRUSH

Use clean paint brushes (suitable for water-based paints). Apply with full brush and spread out evenly.

## SPRAY

Sealfas® Coating may be airless spray applied. For spray equipment information please consult Airless Spray Recommendations or contact your airless spray equipment supplier. Average viscosity range: 55,000 – 75,000 cps. Corrosion resistant pumps and fittings are suggested.

## TOP COATING

If Sealfas® Coating 30-36™ is to be top coated with anything other than an alkyd enamel conforming to DOD-E-24607 as specified in MIL-A-3316C, the user must confirm by his own tests that the products are compatible and that the final results are satisfactory.

## CLEAN UP

Use clean fresh water for cleaning brushes and equipment before product dries. Dry product may be removed with hot soapy water or strong solvents such as chlorinated solvent (non-flammable) or mineral spirits (flammable).

### DATA REPRODUCED FROM UNDERWRITERS' LABORATORIES, INC. BUILDING MATERIALS DIRECTORY

<b>COATING, GENERAL PURPOSE</b>	R-3593
<b>H.B. Fuller Company</b>	
	Surface Burning Characteristics 1/4 inch (6.4 mm) Inorganic Reinforced Cement Board
Surface Flame Spread:	10
Smoke Developed:	5
Number of Coats:	1
Rate per Coat (sq. ft. per gal.):	40

## CUSTOMER SERVICE: 800-832-9002

IMPORTANT: H.B. Fuller Construction Products Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser or as otherwise provided on the certificate of analysis.

**For professional use only. Keep out of reach of children.  
Consult Safety Data Sheet and container label for further information.**