

PROPERTIES

COLOR:

White

APPLICATION CONSISTENCY:

Brush or spray

AVERAGE WEIGHT / U.S. GALLON (ASTM D1475):

10.4 lbs. (1.25 kg/l)

AVERAGE NON-VOLATILE (ASTM D2369):

40% by volume (51% by weight)

COVERAGE RANGE:

Subject to the type of surface being coated. Wet coverages shown below are for smooth non-porous surfaces. Porous or rough surfaces may require higher gallonage to attain required dry thickness.

40 – 70 sq. ft. per gal. (1.0 – 1.7 m²/l) per coat

0.040 in. – 0.023 in. wet film thickness (1.0 – 0.6 mm) per coat

DRYING TIME 73°F (23°C) 50% RH:

Set to Touch: 2 Hours

Dry Through: 15 Hours

SERVICE TEMPERATURE LIMITS:

Temperature at coated surface

0°F to 180°F (-18°C to 82°C)

WATER VAPOR PERMEANCE (TYPICAL AVERAGE):

ASTM F1249: 0.5 to 1.3 perms (0.9 metric perms) at 31 mils dry film thickness (0.8 mm)

WET FLAMMABILITY:

No flash to boiling, 212°F (100°C)

FUNGAL RESISTANCE (ASTM D5590):

Rating = 0

SURFACE BURNING CHARACTERISTICS (ASTM E84):

Flame Spread: 10

Smoke Developed: 5

Tested at coverage rate of 40 sq. ft./gal. (1.0 m²/l). Applied to 1/4 inch (6.4 mm) inorganic reinforced cement board. The flame spread may vary at different product thicknesses and/or when applied over other surfaces.

LIMITATIONS:

Store and apply between 40°F (4°C) and 100°F (38°C), protect from freezing until dry.

Always test foil and paper facings for acceptable adhesion before using.

This product does not protect users or others against bacteria, viruses, germs or other disease organisms. It does not take the place of normal cleaning and disinfecting procedures.

FOSTER® SEALFAS® COATING 30-36AF (Fungus Resistant)

Foster® Sealfas® Coating 30-36AF is a specially formulated white, tough, washable, abrasion-resistant indoor coating for use over thermal insulation in areas where high humidity and elevated temperatures are a problem. It is designed to resist mold, fungus and mildew growth on its surface and protect the insulation system. It is also used as a lagging and a lap adhesive for canvas and glass lagging cloth where additional fungal resistance of the adhesive is required. It has excellent brushing characteristics, which will result in better coverage and more uniformly coated surfaces. It presents a neat white finish, and will not yellow or discolor with age. The surface can be washed free of grease, oil, soot and other dirt accumulation.

Sealfas® Coating 30-36AF provides a protective finish for insulation on air conditioning ducts and cold water piping when applied with canvas, glass cloth or 10x10 glass mesh embedded between two coats. For un-faced insulation or for exterior applications when relative humidity exceeds 75% for continuous periods, a fungus-resistant vapor barrier such as Foster 30-80AF or 60-95 is suggested.

Sealfas® Coating 30-36AF offers the same proven qualities of standard Foster Sealfas® Coating 30-36 with the added benefit of excellent fungus resistance. It meets the performance requirements of MIL-A-3316C, Class 1, Grade A.

Sealfas® Coating 30-36AF meets NFPA 90A and 90B 25/50 requirements and is compatible with polystyrene and polyurethane foam insulations.

Sealfas® Coating 30-36AF meets the requirements of:

- MAS Certified Green®
- California Dept. of Public Health Standard Method v1.2
- VOC Emissions and Content requirements to contribute to **LEED v4** EQ Credit: Low Emitting Materials – Paints and Coatings
- Collaborative for High Performance Schools EQ 7.1

VOC Content: 17 g/l, less water and exempt solvents.



™ Trademark of H.B. Fuller Construction Products Inc.

Visit us on the web at www.fosterproducts.com

APPLICATION GUIDE FOR FOSTER® SEALFAS® COATING 30-36AF

MATERIAL PREPARATION

DO NOT THIN. Apply only to clean, dry, oil-free surfaces. Keep container closed when not in use.

APPLICATION

1. Apply a tack coat of Foster® 30-36AF at 60 – 70 sq. ft. per gal. (1.5 – 1.7 m²/l).
2. Immediately imbed the selected lagging fabric into the wet coating. Smooth to avoid wrinkles and overlap seams by at least 2 inches (5 cm).
3. Immediately apply a finish coat at 60 – 70 sq. ft. per gal. (1.5 – 1.7 m²/l). The dry film thickness of this application will vary with the fabric selected.

For air conditioning ducts, increase the coverage rate to 40 – 50 sq. ft. per gal. (1.0 – 1.2 m²/l) for each coat.

BRUSH

Use clean paint brushes (suitable for water-based paints). Apply with full brush and spread out evenly.

SPRAY

Foster® 30-36AF may be airless spray applied. For spray equipment information please consult Airless Spray Recommendations or contact your airless spray equipment supplier. Average viscosity range: 55,000 – 75,000 cps. Corrosion resistant pumps and fittings are suggested.

TOP COATING

If Foster® 30-36AF is to be top coated with anything other than an alkyd enamel conforming to DOD-E-24607 as specified in MIL-A-3316C, the user must confirm by his/her own tests that the products are compatible and that the final results are satisfactory.

CLEAN-UP

Use clean fresh water for cleaning brushes and equipment before product dries. Dry product may be removed with hot soapy water or strong solvents such as chlorinated solvent (non-flammable) or mineral spirits (flammable).

DATA REPRODUCED FROM UNDERWRITERS' LABORATORIES, INC. BUILDING MATERIALS DIRECTORY

COATING, GENERAL PURPOSE	R-3593
H.B. Fuller Company	
	Surface Burning Characteristics
	1/4 inch (6.4 mm) Inorganic Reinforced Cement Board
Surface Flame Spread:	10
Smoke Developed:	5
Number of Coats:	1
Rate per Coat (sq. ft. per gal.):	40

CUSTOMER SERVICE: 800-832-9002

IMPORTANT: H.B. Fuller Construction Products Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser or as otherwise provided on the certificate of analysis.

**For professional use only. Keep out of reach of children.
Consult Safety Data Sheet and container label for further information.**