

VAPOR RETARDER AND WEATHERPROOFING COATING FOR INTERIOR AND EXTERIOR APPLICATIONS

DESCRIPTION

ENCACEL® X CP-40 is an elastomeric, polymer-based coating designed for the protection of thermal insulation. ENCACEL® X CP-40 vapor retarder coating has good vapor retarder properties as well as excellent low temperature flexibility, resistance to chemicals and excellent weather barrier characteristics.

USES

ENCACEL® X CP-40 vapor retarder coating provides a tough, flexible, fire-resistant finish. It is recommended for hot and cold exterior applications where the chemical environment necessitates additional protection.

It is not to be used in direct contact with polystyrene foam insulation. It may be used with most other types of insulation.

APPLICATION

ENCACEL® X CP-40 vapor retarder coating is applied by trowel. It has excellent bridging properties and will provide a smooth finish, even over relatively rough substrates. For optimum results, it is suggested that ENCACEL® X CP-40 vapor retarder coating be stored at a minimum of 50°F (10°C) before use. For spray or brush applications, the use of ENCACEL® V CP-45 vapor barrier coating is recommended.

Outdoor horizontal surfaces must always drain completely. A pitch of at least 1/2" per foot (4 cm/m) is recommended.

ADVANTAGES

- ENCACEL® X CP-40 vapor retarder coating has excellent tensile and elongation properties, which, coupled with good adhesion and cohesive qualities, make it especially suitable for equipment or systems that cycle.
- ENCACEL® X CP-40 vapor retarder coating will not check or crack in exterior applications.
- The cured film of ENCACEL® X CP-40 Vapor Retarder Coating is fire-resistive and tough, yet flexible.
- It is resistive to many acids and alkalis.

CERTIFIED.

- This product has been tested according to ASTM E84 (Surface Burning Characteristics of Building Materials).

™ Trademark of H.B. Fuller Construction Products Inc.

Visit us on the web at www.fosterproducts.com

COLOR

CP-40: White, trowel/glove
CP-40-1: Gray, trowel/glove

WET WEIGHT (ASTM D1475)

10.4 lbs./U.S. gal. (1.3 kg/liter)

AVERAGE NON-VOLATILE (ASTM D2369)

40% to 44% by volume (60% by weight)

SERVICE TEMPERATURE RANGE

Temperature to which dry film is subjected.
-50°F to 220°F (-46°C to 104°C)

APPLICATION AND STORAGE TEMPERATURE RANGE

40°F to 100°F (4°C to 38°C)

DRYING TIME

Drying time will vary depending upon film thickness, temperature and humidity.

To Touch: 5 Hours
Through: 48 Hours

COVERAGE

Varies with substrate, service type and service temperature of system.
5 gal./100 sq. ft. (2.0 l/m²)

CLEAN UP

Xylene

WATER VAPOR PERMEANCE (TYPICAL AVERAGE)

ASTM F1249: 0.03 perms at 30 mils dry. Tested at 100°F (38°C) and 90% RH

SURFACE BURNING CHARACTERISTICS (ASTM E84)



GENERAL PURPOSE COATING
SURFACE BURNING CHARACTERISTICS

Applied to 1/4" Inorganic Reinforced Cement Board

Flame Spread:	10
Smoke Developed:	15
Rate per Coat (sq. ft./gal.):	25
Number of Coats:	1
Flash Point of Liquid Coating (Closed Cup):	125°F (51.7°C)

282U

H.B. Fuller Construction Products Inc.

Customer Service
800-832-9002

1105 South Frontenac St.
Aurora, IL 60504

Fax
800-952-2368

GENERAL SPECIFICATIONS

Mastic finish over insulation shall be ENCACEL® X CP-40 vapor retarder coating. It shall be applied in two coats, the first coat being a tack coat applied at a coverage rate of 2 U.S. gallons per 100 sq. ft. (0.81 l/m²). While still wet, a layer of CHIL-GLAS® #10 glass fiber reinforcing mesh shall be embedded, with all fabric seams overlapped a minimum of 2" (5.08 cm). A finish coat, at a coverage rate of 3 U.S. gallons per 100 sq. ft. (1.22 l/m²), shall then be applied. There shall be no voids or holidays, and the mastic shall be troweled or wet-brushed to a smooth, even finish. When applied in this fashion, the wet film thickness shall equal 0.090" (2.3 mm), and the resulting dry film will equal at least 0.038" (1.0 mm).

All adjoining, uninsulated surfaces must be completely waterproofed and flashed by extending the ENCACEL® X CP-40 vapor retarder coating and glass fiber reinforcing mesh a minimum of 4" (10.16 cm) onto the adjoining surfaces. If those surfaces will attain temperatures between 180°F and 300°F (82°C to 149°C), use CHIL-BYL® CP-76 joint sealant as the flashing compound. **When using a solvent-based vapor retarder coating such as ENCACEL® X CP-40, the joint sealant to be used shall be CHIL-BYL® CP-76.** CHIL-JOINT® CP-70 joint sealant may result in some discoloration of the dry film.

1. For areas subject to severe mechanical or physical abuse, tack coat coverage shall be 4 U.S. gallons per 100 sq. ft. (1.62 l/m²). The finish coat shall be applied at a coverage rate of 4 U.S. gallons per 100 sq. ft.
2. Alternate Finish for Cryogenic Design: Tack coat coverage shall be 3 gallons per 100 square feet (1.62 l/m²). Glass fiber reinforcing mesh shall be CHIL-GLAS® #10. A second coat shall be applied at a coverage rate of 4 gallons per 100 sq. ft. (1.62 l/m²). After a minimum 24 hour drying time, an additional coat of ENCACEL® X CP-40 vapor retarder coating shall be applied at a coverage rate of 4 U.S. gallons per 100 sq. ft. (1.62 l/m²).

Application Guide and Suggested Procedures

1. USE OF MATERIAL

ENCACEL® X CP-40 vapor retarder coating is designed for trowel or palm applications. **DO NOT THIN.** ENCACEL® X CP-40, being solvent-based, is not harmed by freeze-thaw cycling. However, applications at temperatures below 40°F (4°C) will inhibit its normal drying cycle. ENCACEL® X CP-40 vapor retarder coating will not freeze; however, it is recommended that long-period storage be done in a heated area. For large surface areas, ENCACEL® V CP-45 vapor retarder coating is available for spray application.

2. THE CONDITION OF THE INSULATION TO BE COATED

The best coating in the world is no better than the surface to which it is applied. **Know the type and condition of the substrate.** ENCACEL® X CP-40 is a vapor retarder coating. It should **never** be applied over damp or wet insulation. ENCACEL® X CP-40 vapor retarder coating can be used over hot insulation, but the following procedures must always be undertaken:

1. Surface to be coated must be thoroughly dry.
2. To assure proper bonding, fibrous and calcium silicate type insulations should be primed with Childers® CHIL-SEAL® CP-50A MV1 diluted 50% with water. The CHIL-SEAL® CP-50A MV1 adhesive must be completely dry before applying ENCACEL® X CP-40 vapor retarder coating.

3. APPLICATION

ENCACEL® X CP-40 vapor retarder coating can be applied with trowel or glove. It is not self-leveling, but a smooth finish may be obtained by smoothing the surface with a clean brush dampened with detergent foam.

In applications where insulation has been fabricated with asphalt as the adhesive or where asphalt has been used as a joint sealant, there likely will be discoloration of the ENCACEL® X CP-40 vapor retarder coating film. This discoloration will not affect the overall physical properties of the dry film; however, if the discoloration would be objectionable, use of an alternate sealant adhesive is suggested. Foster® 81-84NH adhesive will not discolor ENCACEL® X dry film.

CUSTOMER SERVICE: (800) 832-9002

IMPORTANT: H.B. Fuller Construction Products Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser or as otherwise provided on the certificate of analysis.

**For professional use only. Keep out of reach of children.
Consult Safety Data Sheet and container label for further information.**