



## PROPERTIES

**COLOR:**

Black

**APPLICATION CONSISTENCY:**

Air atomized spray, brush, roller or duct liner machine

**AVERAGE WEIGHT / U.S. GALLON (ASTM D1475):**

8.9 lbs. (1.07 kg/l)

**AVERAGE NON-VOLATILE (ASTM D2369):**

51% by volume (52% by weight)

**COVERAGE RANGE:**

Subject to type of surface and material being bonded.

**Spray:** approx. 300 – 500 sq. ft./gal. (7.4 – 12.3 m<sup>2</sup>/l)

**Brush/Roller:** 150 – 300 sq. ft./gal. (3.7 – 7.4 m<sup>2</sup>/l)

**BONDING TIME RANGE:**

Dependent on temperature and humidity.

0 – 10 minutes

**SERVICE TEMPERATURE LIMITS:**

Temperature at coated surface.

-20°F to 200°F (-29°C to 93°C)

**WET FLAMMABILITY:**

No flash to boiling, over 200°F (93°C)

**SURFACE BURNING CHARACTERISTICS (ASTM E84):**

Flame Spread: 0

Smoke Developed: 0

Tested at coverage rate of 300 sq. ft./gal. (7.4 m<sup>2</sup>/l).

Applied to 1/4 inch (6.4 mm) inorganic reinforced cement board. The flame spread may vary at different product thicknesses and/or when applied over other surfaces.

## FOSTER® JAC-TAC® ADHESIVE AND EDGE SEALER

**Foster® JAC-TAC® Adhesive** is a black, rapid-setting, resin/polymer emulsion adhesive for use with low density fibrous glass insulation, duct wrap and acoustical linings (up to 3 lbs./c.f.) in air handling systems. It has good wet grab and can be applied to painted or unpainted steel, galvanized steel or aluminum surfaces.

**JAC-TAC® Adhesive** is formulated for use in duct liner machines, both air atomized spray and roll coater types. It has excellent hot peel strength and high humidity resistance. Once dry and cured, it has outstanding water resistance.

**JAC-TAC® Adhesive** is water-based and non-flammable in the wet state. It meets the requirements of ASTM C916-85, Type II (ASC-A-7001, Type II).

**JAC-TAC® Adhesive** is also used to seal or butter cut edges of duct liner insulation to retard fiber release. It can be applied to edges by brush or spray and its black color matches the original facing surface.

**JAC-TAC® Adhesive** meets NFPA 90A & 90B 25/50 requirements.

**JAC-TAC® Adhesive 85-62™** meets the requirements of:

- MAS Certified Green®
- California Dept. of Public Health Standard Method v1.2
- VOC Emissions and Content requirements to contribute to **LEED v4** EQ Credit: Low Emitting Materials – Paints and Coatings
- Collaborative for High Performance Schools EQ 7.1

VOC Content: 6 g/l, less water and exempt solvents.



### LIMITATIONS

Store and apply between 40°F (4°C) and 100°F (38°C), protect from freezing until dry.

Always test plastic foam insulation for warpage when using any water-based adhesive.

Not suggested for sealing vapor barrier jackets.

Overhead applications may require mechanical fasteners.

™ Trademark of H.B. Fuller Construction Products Inc.

Visit us on the web at [www.fosterproducts.com](http://www.fosterproducts.com)

**H.B. Fuller Construction Products Inc.**

6107 Industrial Way • Houston, TX 77011 • 833-849-3700

# APPLICATION GUIDE FOR FOSTER® JAC-TAC® ADHESIVE 85-62™

## MATERIAL PREPARATION

Stir well. DO NOT THIN. Apply only to clean, dry, oil-free surfaces. Keep container closed when not in use.

## APPLICATION

### Spray:

Apply the Foster® JAC-TAC® adhesive to the metal surface uniformly at 300 – 500 sq. ft./gal. (7.4 – 12.3 m<sup>2</sup>/l). While still wet, press the insulation into place, making sure that complete contact is made with applied adhesive.

Average viscosity range: 1,000 – 2,000 cps. Before using for the first time, existing spray systems must be completely cleaned and free of the old adhesive and solvents. Corrosion resistant pumps and fittings are suggested.

The following equipment combinations are suggested:

	MODEL SPRAYGUN	FLUID NOZZLE	AIR CAP	FLUID PRESSURE	ATOMIZATION PRESSURE
Binks	62	63	66SD	20 – 25 psi	60 – 70 psi
DeVilbiss	JGA	FX	770	20 – 25 psi	60 – 70 psi
Graco	Siphon	0.070	208765B	Siphon	60 psi

Not recommended for airless spray application.

### Brush/Roller:

Use clean equipment suitable for water-based paints.

## CLEAN UP

To clean up, use warm soapy water if still wet. When dry, use xylene (flammable) or chlorinated solvent (non-flammable).

### DATA REPRODUCED FROM ASTM E84 FIRE TEST (TUNNEL TEST)

#### ADHESIVES

H.B. Fuller Company SURFACE BURNING CHARACTERISTICS

Applied to 1/4 inch (6.4 mm) Inorganic Reinforced Cement Board

Surface Flame Spread: 0

Smoke Developed: 0

Number of Coats: 1

Rate Per Coat (sq. ft. per gal.): 300

## CUSTOMER SERVICE: 833-849-3700

IMPORTANT: H.B. Fuller Construction Products Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser or as otherwise provided on the certificate of analysis.

For professional use only. Keep out of reach of children.

Consult Safety Data Sheet and container label for further information.

Foster PDS 85-62 R0719 NP