



**90-61**

**Product Data Sheet**

## PROPERTIES

**COLOR:**

Dark grey

**APPLICATION CONSISTENCY:**

Brush or trowel

**AVERAGE WEIGHT/U.S. GALLON (ASTM D1475):**

9.3 lbs./gal. (1.11 kg/l)

**AVERAGE NON-VOLATILE (ASTM D2369):**

45.0% by volume (57.5% by weight)

**COVERAGE RANGE:**

Subject to type of surface being coated.

3.5 to 4.0 gal./100 sq. ft. (1.43 to 1.63 l/m<sup>2</sup>) on a smooth non-porous surface. Porous or rough surfaces will require higher gallonage to attain required dry thickness

**Dry Thickness:**

0.025 to 0.028 in. (0.64 mm to 0.71 mm)

**Equivalent Wet Coverage:**

0.056 in. to 0.064 in. (1.42 mm to 1.63 mm)

**DRYING TIME 73°F (23°C) 50% RH:**

Temperatures below 70°F (21°C) may require longer dry times.

To Touch: 2 – 3 Hours

Through: 24 Hours

**SERVICE TEMPERATURE LIMITS:**

Temperature at coated surface.

-320°F to 250°F (-196°C to 121°C)

**WATER VAPOR PERMEANCE (TYPICAL AVERAGE):**

ASTM F1249: < 0.01 perms (< 0.0066 metric perm) at 0.020 – 0.025 in. (0.51 – 0.64 mm) dry film thickness when tested at 100°F and 90% RH

**SAFETY:**

Flash point: 115°F (46°C)

## FOSTER CRYOLAR™ 1K VAPOR STOP SEALANT

**FOSTER Cryolar™ 1K Vapor Stop** is a ready-to-use, one-component, vapor stop sealant for use in cryogenic applications. It is specially formulated with select synthetic rubbers to form an elastomeric, vapor barrier film capable of spanning the temperature ranges found in cryogenic applications including LNG, ethylene and ammonia production. It is suitable for application to PUR and PIR foam, cellular glass and other rigid insulations in conjunction with aluminum, steel and masonry construction materials.

**Cryolar™ 1K Vapor Stop** has excellent resistance to moisture and water vapor, forming a vapor tight seal from the cryogenic pipe surface to the ambient outer insulation surface.

**Cryolar™ 1K Vapor Stop** is designed for vapor stop applications on insulated cryogenic pipelines and equipment. It can also be used on very low temperature applications to seal seams where a water vapor tight insulation system is required.

**Cryolar™ 1K Vapor Stop** is manufactured at an ISO 9001 Quality System Certified Facility.

**LIMITATIONS**

Store and apply between 40°F (4°C) and 100°F (38°C).

Always test plastic materials for compatibility when using a solvent-based product. Do not use on polystyrene insulation.

Always allow the sealant to dry completely before covering with impermeable materials.

Not suggested as an exposed sealant for extended periods of time.

Use caution when installing peel and stick membranes directly over 90-61. Removing or repositioning will damage the vapor stop surface.

™ Trademark of H.B. Fuller Construction Products Inc.

**Visit us on the web at [www.fosterproducts.com](http://www.fosterproducts.com)**

**H.B. Fuller Construction Products Inc**

1105 South Frontenac St ○ Aurora, IL 60504 ○ (800) 832-9002 ○ fax (800) 952-2368

**APPLICATION GUIDE  
FOR  
FOSTER® CRYOLAR™ 1K VAPOR STOP  
90-61**

**MATERIAL PREPARATION**

Stir well. DO NOT THIN. Apply only to clean, dry surfaces. Keep container closed when not in use to prevent solvent evaporation.

**APPLICATION**

Apply a tack coat at 2 gal./100 sq. ft. (0.8 l/m<sup>2</sup>), 31 mils (0.8 mm) wet film. Embed Foster Mast-a-Fab® reinforcing mesh, being sure to smooth all wrinkles and allow to set. Follow with a finish coat of 90-61 sealant at a rate of 2 gal./100 sq. ft. (0.8 l/m<sup>2</sup>), 31 mils (0.8 mm) wet film. Reinforcing mesh must be used for cryogenic applications. Finished dry film shall be 23 mils (0.9 mm) dry film thickness minimum.

**CLEAN UP**

Use solvents such as chlorinated solvents (non-flammable) or MEK (flammable) for cleaning tools and equipment. Completely clean all equipment before sealant sets up.

**CUSTOMER SERVICE: (800) 832-9002**

IMPORTANT: H.B. Fuller Construction Products Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser or as otherwise provided on the certificate of analysis.

**For professional use only. Keep out of reach of children.  
Consult Safety Data Sheet and container label for further information.**