

LAGGING ADHESIVE AND SIZING FOR INSULATION

DESCRIPTION

CHIL-LAG® CP-52C Adhesive is a lagging adhesive, which is easy to apply by brush or spray. In sizing applications, it may also be dipped. It is a water-based, fire-resistive material.

USES

CHIL-LAG® CP-52C Adhesive is used to adhere the laps of canvas and glass cloths used as lagging fabrics over thermal insulation. It is also used as a sizing for these lagging cloths.

ADVANTAGES

CHIL-LAG® CP-52C Adhesive, when dry, results in a permanent adhesive bond superior to sewing or stapling. CHIL-LAG® CP-52C Adhesive adheres fabrics to insulation substrates and will shrink canvas down tightly to the surface and seal the fabric for further painting where required.

APPLICATION

CHIL-LAG® CP-52C Adhesive is easy to apply by brush, spray or dipping. Most applications are by brush. For dipping applications, dilute 4 parts CP-52C to 1 part water. Not suggested for outdoor exposure.

CERTIFIED

- MAS Certified Green®
- California Dept. of Public Health Standard Method v1.2
- VOC Emissions and Content requirements to contribute to **LEED v4** EQ Credit: Low Emitting Materials – Paints and Coatings
- VOC Content: 69 g/l, less water and exempt solvents
- Collaborative for High Performance Schools EQ 7.1
- Meets the requirements of NFPA Standard 90A and 90B



™ Trademark of H.B. Fuller Construction Products Inc.

Visit us on the web at www.fosterproducts.com

COLOR

White

WET WEIGHT (ASTM D1475)

11.2 lbs./U.S. gal. (1.3 kg/liter)

AVERAGE NON-VOLATILE (ASTM D2369)

51% by weight

SERVICE TEMPERATURE RANGE

Temperature to which dry film is subjected.
-20°F to 180°F (-29°C to 82°C)

APPLICATION TEMPERATURE RANGE

40°F to 100°F (4°C to 38°C)

DRYING TIME

Drying time will vary depending upon film thickness, temperature and humidity.

To Touch: ½ Hour

Through: 8 Hours

COVERAGE

Coverage will vary with substrate & membrane.

1.0 – 1.25 U.S. gal./100 sq. ft. (0.4 – 0.5 l/m²) per coat on canvas

1.25 – 2.5 U.S. gal./100 sq. ft. (0.5 – 1.0 l/m²) per coat on brattice cloth

1.0 U.S. gal./100 sq. ft. (0.4 l/m²) per coat on smooth, dense surfaces

CLEAN UP

Warm, soapy water

SURFACE BURNING CHARACTERISTICS (ASTM E84)



GENERAL PURPOSE COATING
SURFACE BURNING CHARACTERISTICS
282U

Applied to ¼" Inorganic Reinforced Cement Board

Flame Spread:	10
Smoke Developed:	0
Number of Coats:	1
Rate per Coat (sq. ft./gal.):	100
Flash Point of Liquid Coating (Closed Cup):	No flash

R3593

H.B. Fuller Construction Products Inc.

Customer Service
800-832-9002

1105 South Frontenac Street
Aurora, IL 60504

Fax
800-952-2368

CANVAS LAGGING ON PIPE INSULATION

Laps of factory-applied, canvas jackets shall be adhered by applying a brush coat of CHIL-LAG® CP-52C Adhesive at a coverage rate of not less than 1 U.S. gal./100 sq. ft. (0.4 liters/m²).

To shrink and size canvas, a brush coat of CHIL-LAG® CP-52 C Adhesive shall be applied to the entire surface.

CANVAS LAGGING FOR LARGE PIPES (FIELD-APPLIED), DUCTS AND EQUIPMENT

After the insulation has been installed, a heavy brush coat shall be applied to the entire surface. The canvas shall be immediately embedded into the wet adhesive. A finish sizing coat at a minimum coverage of 1 gallon per 100 sq. ft. (0.4 l/m²) shall be applied over the fabric.

NOTES TO SPECIFYING ENGINEER

1. The above specified finish is primarily a sizing and where appearance is not the primary factor. For a tougher, smoother appearing finish, CHIL-SEAL® CP-50A as a combination lagging adhesive and coating is recommended.
2. Where appearance is the primary factor, and particularly where open weave glass cloth or other heavy, coarse fabrics are being used, it is recommended that VI-CRYL® CP-11 Coating be used as the finish for maximum appearance and smoothness.

Application Guide and Suggested Procedures

1. USE OF MATERIAL

CHIL-LAG® CP-52C Adhesive brushes easily. Thinning is not recommended when CHIL-LAG® CP-52C Adhesive is used as an adhesive. It may be thinned when canvas is being dipped.

It is recommended that CHIL-LAG® CP-52C Adhesive be stored in a heated warehouse. It should never be applied at temperatures below 40°F (4°C).

2. THE CONDITION OF THE INSULATION TO BE ADHERED OR COATED

Dusty or loose, fibrous surfaces should first be primed before using CHIL-LAG® CP-52C as an adhesive for securing lagging cloths to insulation. The surfaces shall be primed with a solution of CHIL-LAG® CP-52C diluted 50% with water.

3. APPLICATION

CHIL-LAG® CP-52C Adhesive is normally applied with any type of paintbrush. In some areas, dipping of canvas or other fabrics is desired. For these applications, the CHIL-LAG® CP-52C Adhesive may be diluted (4 parts CP-52C to 1 part water). The canvas or other fabric is dipped into the bucket of diluted lagging adhesive after which about 50% of the mixture is wrung out and the wet cloth wrapped around the pipe, duct or surface to be lagged.

4. DRYING AND TOP COATING

CHIL-LAG® CP-52C Adhesive dries quite rapidly. However, it should not be top coated in less than 12 hours, and user should make sure that it is completely dry before top coating.

CUSTOMER SERVICE: (800) 832-9002

IMPORTANT: H.B. Fuller Construction Products Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser or as otherwise provided on the certificate of analysis.

**For professional use only. Keep out of reach of children.
Consult Safety Data Sheet and container label for further information.**