

PROPERTIES

COLOR:

White, Gray or Black

APPLICATION CONSISTENCY:

Brush, Trowel, Glove or Power Extrusion

AVERAGE WEIGHT / U.S. GALLON (ASTM D1475):

12.0 lbs. (1.44 kg/l)

AVERAGE NON-VOLATILE (ASTM D2369):

69% by weight

COVERAGE RANGE:

Brush: 45 – 55 sq. ft./gal. (1.10 – 1.35 m²/l)
0.036 – 0.029 in. (0.9 – 0.7 mm) wet film thickness

DRYING TIME 73°F (23°C) 50% RH:

Set to Touch: 1 hour
Dry Through: 16 hours

SERVICE TEMPERATURE LIMITS:

20°F to 200°F (-7°C to 93°C)

WET FLAMMABILITY:

No flash to boiling, 210°F (99°C)

SURFACE BURNING CHARACTERISTICS (ASTM E84):

Flame Spread: 20
Smoke Developed: 15
Tested at coverage rate of 45 sq. ft. per gal. (1.1 m²/l) in a 3 in. (7.6 cm) strip. Applied to rigid fiberglass duct board. Type 475, covered with foil/scrim/kraft paper facing material.



UL 181A-M
UL 181B-M
6P84

AIR-TIGHT™ FDS-181 DUCT SEALANT

AIR-TIGHT™ 181 DUCT SEALANT is a fire-resistive, fibrated, water-based sealant for indoor or outdoor low, medium and high velocity heating and air conditioning ducts. It performs as a tough and flexible adhesive and sealant, forming a durable seal against air leakage when used with reinforcing membrane. Mechanical fasteners of the type and number normally used for duct assemblies are required to provide rigidity to the duct system.

AIR-TIGHT™ 181 DUCT SEALANT is excellent for duct closure and butt joint seam sealing on both flexible and rigid faced fiberglass duct systems. It is non-flammable and has a mild odor when wet. It dries odor free.

AIR-TIGHT™ 181 DUCT SEALANT is ideal for vapor sealing ASJ, FRK and FSK jackets and board facings on rigid duct board at joints, laps and over staple and punctures.

AIR-TIGHT™ 181 DUCT SEALANT meets NFPA 90A and 90B 25/50 requirements.

AIR-TIGHT™ 181 DUCT SEALANT meets all SMACNA pressure classes up to 10" w.g. and SMACNA seal classes A, B and C on ducts constructed to SMACNA standards.

AIR-TIGHT™ 181 DUCT SEALANT has low VOC content and meets requirements of:

- MAS Certified Green®
- California Dept. of Public Health Standard Method v1.2
- VOC Emissions and Content requirements to contribute to **LEED v4** EQ Credit: Low Emitting Materials – Paints and Coatings
- VOC Content: 26 g/l, less water and exempt solvents
- Collaborative for High Performance Schools EQ 7.1
- SCAQMD Rule 1168



™ Trademark of H.B. Fuller Construction Products

Visit us on the web at www.fosterproducts.com

LIMITATIONS

Store and apply between 40°F (4°C) and 100°F (38°C), protect from freezing until dry.

H.B. Fuller Construction Products

APPLICATION GUIDE FOR AIR-TIGHT™ 181 DUCT SEALANT FDS-181 UL 181A-M & 181B-M LISTED

MATERIAL PREPARATION

DO NOT THIN. Apply only to clean, dry, oil-free surfaces. Keep container closed when not in use.

APPLICATION

UL 181A MASTIC CLOSURE OF UL 181 RIGID FIBERGLASS AIR DUCTS:

Apply to the surface by brush, trowel or power extrusion. Uniformly brush out at 3" – 4" wide tack coat over the stapled and smoothed joint at the nominal rate of 1.12 gal./100 sq. ft. (0.46 l/m²). Embed the reinforcing membrane into the tack coat, taking care that all of the mesh is filled. Pull the membrane taut and apply a second coat at the nominal rate of 1.12 gal./100 sq. ft. (0.46 l/m²). Allow the completed joint to dry at least 24 hours above 70°F (21°C) before pressure testing. High humidities (over 70%) and/or cooler temperatures may retard drying. Total (mastic plus scrim plus mastic) wet film thickness to be 36 mils. Fiberglass scrim to be 5 mils thick, 20x10 plain weave weighing 1.75 oz/yd² (59 g/m²).

UL 181B MASTIC CLOSURE OF UL 181 FLEXIBLE AIR DUCTS:

Apply to clean, dry, oil-free surface by brush, trowel or power extrusion. Uniformly brush out at 2" wide coat over the joint at the nominal rate of 1.87 gal./100 sq. ft. (0.76 l/m²). Total coverage rate to be 53.5 sq. ft./gal. (1.31 m²/l). Allow the completed joint to dry at least 24 hours above 70°F (21°C) before pressure testing. High humidities (over 70%) and/or cooler temperatures may retard drying. Total wet film thickness to be 30 mils (0.76 mm).

OTHER DUCT CLOSURE AND SEALING APPLICATIONS – NOT UL 181 LISTED:

For other applications or on different types of low velocity metal duct construction, the use of a reinforcing membrane is optional. (Reinforcing membrane is suggested in medium and high pressure applications.) Apply at a rate of 50-55 sq. ft./gal. (1.23 – 1.35 m²/l). Allow the completed joint to dry at least 24 hours above 70°F (21°C) before pressure testing. High humidities (over 70%) and/or cooler temperatures may retard drying. For best results, do not exceed 1/4" (6.4 mm) wet film thickness. AIR-TIGHT™ Duct Sealant has excellent weather, water and U.V. resistance, allowing it to be used outdoors and in high humidity environments.

LIMITATIONS: Always test foil and paper facings for acceptable adhesion before using. Outdoor horizontal surfaces must always drain completely. A pitch of at least 1/4" per foot (2 cm/m) is required. To resist rain washoff, allow at least 12 – 15 hours drying time above 40°F (4°C), with a relative humidity of 50%. Higher humidity or lower temperatures may retard drying.

POWER EXTRUSION:

AIR-TIGHT™ 181 Duct Sealant may be applied using a wide variety of power (pressure) extrusion equipment suitable for use with water-based sealants. It is a soft buttery gel with a typical viscosity range of 130,000 – 150,000 cps for 95-90. Corrosion resistant pumps and fittings are suggested.

CLEAN UP

Use fresh water to clean brushes and equipment before product dries. Dry product may be removed with hot soapy water or strong solvents such as chlorinated solvent (non-flammable) or mineral spirits (flammable).

CUSTOMER SERVICE: 800-832-9002

IMPORTANT: H.B. Fuller Construction Products warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser or as otherwise provided on the certificate of analysis.

**For professional use only. Keep out of reach of children.
Consult Safety Data Sheet and container label for further information.**