

FOSTER FACING AND LAMINATING ADHESIVE

DESCRIPTION


This adhesive was developed to bond various facing materials to fiberglass blankets. This product has been composite tested and meets the Fire Hazard Classification 25/50 with a wide variety of facing/fiberglass laminates.

TYPICAL PHYSICAL PROPERTIES AND GENERAL INFORMATION

Solids (1):	43 to 45%
Viscosity (2):	300-700 cps.
PH:	2.5 to 4.5
Weight/gallon:	9.0
Residual Monomer:	0.5 Max %
Appearance:	Milky blue-white
Particle Size Average:	Less than 0.25 microns
Surfactant System:	Anionic
Surface Tension (3) :	36 Dynes/cm
Mechanical Stability (4):	Excellent
Fungal Resistance (5):	Rating "0", no growth
Tg (6):	-9 to -7 degrees C.
Film:	Flexible, water clear, excellent water and solvent resistance.
Clean up:	Water (wet), mineral spirits (dry)

Methods

- (1) Forced air oven 2 hours at 130°C (110°C if modified)
- (2) Brookfield Viscometer Model RVF, at 20 RPM at 25°C.
- (3) P.B. Tensiometer LG-60/40 E/W dilution with water.
- (4) Does not break after 15 minutes at high speed in Waring Blender.
- (5) ASTM G-21
- (6) Differential Thermal Analysis

	ADHESIVES
	SURFACE BURNING CHARACTERISTICS
Applied to Inorganic Reinforced Cement Board	
Flame Spread:	5
Smoke Developed:	15
Tested as applied at a coverage rate of 200 ft ² /gal	
Flash point of liquid adhesive (closed cup): no flash to boiling	
312U	

Store and apply between 40°F (4°C) and 100°F (38°C), protect from freezing until dry.

™ Trademark of H.B. Fuller Construction Products Inc.

Visit us on the web at fosterproducts.com

H.B. Fuller Construction Products Inc.

1105 South Frontenac St o Aurora, IL 60504 o 800-832-9002 o fax 800-942-6856

CUSTOMER SERVICE—800-231-9541 OR 800-338-2975

IMPORTANT: H.B. Fuller Construction Products Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser or as otherwise provided on the certificate of analysis.

**For professional use only. Keep out of reach of children.
Consult Safety Data Sheet and container label for further information.**