

PROPERTIES

COLOR

White

APPLICATION CONSISTENCY

Trowel/Glove/Brush

AVERAGE WEIGHT/U.S. GALLON (ASTM D1475):

11.3 lbs. (1.35 kg/l)

AVERAGE NON-VOLATILE (ASTM D2369):

51% by volume (64% by weight)

COVERAGE RANGE:

Subject to the nature of material coated. Wet coverages shown below are for smooth non-porous surfaces. Porous or rough surfaces will require higher gallonage to attain required dry thickness.

4 to 6 gal./100 sq. ft. (1.6 to 2.4 l/m²)

DRYING TIME:

Set to Touch: 2-4 hours

Dry Through: 24 -36 hours

SERVICE TEMPERATURE LIMITS:

Temperature at coated surface.

-40°F to 200°F (-40°C to 93°C)

WATER VAPOR PERMEANCE (TYPICAL AVERAGE):

>1.0 perms at 1/16 inch (1.6 mm) dry film thickness by ASTM E96, Procedure B

WET FLAMMABILITY:

No flash to boiling

SURFACE BURNING CHARACTERISTICS (ASTM E84)



GENERAL PURPOSE COATING
SURFACE BURNING CHARACTERISTICS
282U

Applied to 1/4" Inorganic Reinforced Cement Board	
Flame Spread:	10
Smoke Developed:	45
Rate per Coat (sq. ft./gal.):	25
Number of Coats:	1
Flash Point of Liquid Coating (Closed Cup):	No flash to boiling

R3593

Visit us on the web at fosterproducts.com

FOSTER® SEALFAS G-P-M® MASTIC

Foster® Sealfas G-P-M® Mastic is a water-based, general purpose mastic having excellent trowel and brush properties. G-P-M® is used for the protection of thermal insulation and hard, dry cement coats, both indoors and outdoors.

It is for use over typical industrial and commercial insulations including faced and unfaced fiberglass, mineral wool, PIR, PUR, cellular glass, phenolic, polystyrene and calcium silicate. It bonds well to most foil laminates for excellent protection of hot and dual service* insulation systems.

Sealfas G-P-M® Mastic is fire-resistive and features ease of application, non-flammability, non-toxicity, mild odor, insulation compatibility, good package stability, plus excellent outdoor durability.

Sealfas G-P-M® Mastic meets NFPA 90A & 90B 25/50 requirements.

Sealfas G-P-M® Mastic is produced under the classification and follow-up service of Underwriter's Laboratories, Inc.

Sealfas G-P-M® Mastic 35-00N meets the requirements of:

- MAS Certified Green®
- California Dept. of Public Health Standard Method v1.2
- VOC Emissions and Content requirements to contribute to **LEED v4** EQ Credit: Low Emitting Materials – Paints and Coatings
- Collaborative for High Performance Schools EQ 7.1

VOC Content: 0 g/l, less water (ASTM D6886)



LIMITATIONS

Store and apply between 40°F (4°C) and 100°F (38°C), protect from freezing until dry.

To resist rain washoff, allow at least 16 hours drying time above 40° F (4°C), with a relative humidity of 50%. Higher humidity at lower temperatures may retard drying.

Always test paper and foil facings for acceptable adhesion before using.

Outdoor horizontal surfaces must always drain completely. A pitch of at least 1/2 inch per foot (4 cm/m) is recommended.

Always select Foster® Sealfas G-P-M® Mastic 35-00N white for use over polystyrene insulation installed outdoors.

* For dual or cold service applications ensure the insulation has an integrated vapor retarder installed under the mastic

APPLICATION GUIDE FOR FOSTER® SEALFAS G-P-M® MASTIC 35-00N

MATERIAL PREPARATION

DO NOT THIN. Foster® Sealfas G-P-M® Mastic will appear to be thick, but this is a "false" consistency which "breaks down" readily on application. Stirring is not necessary. Apply only to clean, dry, oil-free surfaces. Keep container closed when not in use.

APPLICATION – HEAVY DUTY, HOT AND DUAL TEMPERATURE SERVICE

Follow flashing recommendations when installed outdoors.

For best results, prime hygroscopic alkaline cements with Foster® 32-22 Protektor® Sealant or Foster 30-36HF Adhesive/Coating diluted 50% with water to lock down dusty surfaces. Both the cement and the primer must be completely dry before the Foster® Sealfas G-P-M® Mastic is applied.

MAST-A-FAB® REINFORCEMENT

For interior surfaces apply a tack coat of Foster® Sealfas G-P-M® Mastic at a thickness of 1/32 inch (0.8 mm). This is equivalent to 2 gal./100 sq. ft. (0.8 l/m²). Embed Foster® Mast-A-Fab® white membrane into wet tack coat. Smooth membrane to avoid wrinkles and overlap all seams at least 2 inches (5 cm). Apply a finish coat of Foster® Sealfas G-P-M® Mastic at a minimum thickness of 1/32 inch (0.8 mm). This finish coat shall be applied no later than 1/2 hour after the tack coat and shall completely cover the membrane.

For exterior surfaces increase the finish coat to 1/16" (2.4 l/m²) This is equivalent to 4 gal./100 sq. ft. (1.6 l/m²). This application shall provide a minimum dry film thickness of 50 mils (1.2 mm).

HEAVY DUTY APPLICATIONS –GREATER TENSILE STRENGTH

Apply as above, substituting Childers™ Chil-Glas® #5 as the reinforcing membrane. Note that the membrane weave pattern will show through the dried mastic.

TROWEL

Use clean steel trowel. Apply in full thickness promptly. Avoid excessive troweling.

BRUSH

Use a good brush (suitable for water-based paints), making strokes as long as possible over the surface. Apply with full brush and spread out evenly. Do not overwork. Multiple coats will be needed to achieve the minimum dry film thickness.

CLEAN UP

Use fresh water to clean equipment before product dries. Dry product may be removed with hot soapy water or solvents such as chlorinated solvent (non-flammable) or xylol (flammable).

CUSTOMER SERVICE: 800-832-9002

IMPORTANT: H.B. Fuller Construction Products Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser or as otherwise provided on the certificate of analysis.

**For professional use only. Keep out of reach of children.
Consult Safety Data Sheet and container label for further information.**